

June 2000

## **OceanMaster Polygloss Finish**

### Description

The ultimate two-pack polyurethane finish that offers high gloss retention and chemical resistance. May be applied directly onto fibreglass gelcoat, epoxy or polyurethane undercoat.

### For use on

Topside, deck, superstructure and any rigid construction after suitable surface preparation.

### Direction for use

Product designed for application by spray or brush.

Airless Spray	Line Pressure :	100 – 130 Kg sq.cm
	Tip Size :	0.015 – 0.017
	Compression :	30:1
Conventional Spray	Pot Pressure :	40 to 60 PSI
Wet Film Thickness	:	85 microns
Dry Film Thickness	:	40 microns
Coverage	:	11 to 12 sq.m/L
Mixing Ratio	:	3 to 1 by volume
Thinner	:	T300
Recoat	:	6 hrs min
Curing Time	:	48 hrs.
Aged Recoat	:	Sand Surface
Finish	:	Gloss

### Health and Safety

Provide adequate ventilation during use. Avoid contact with skin and eyes. Avoid breathing dust vapour or spray. Wear eye protection and gloves during use.

---