

Jotun Penguard HB

Special Washing Procedure When Used In Tanks For Potable Water

Either:

After the paint is cured (as per specified drying/ curing time), fill the tank with warm water of above 60 – 80 degrees Celsius, letting the water remain in the tank for 24 hours. Finally, either wash the tank thoroughly with brushes, using water of minimum 80 degrees Celsius, or, wash the tank with steam.

Or:

After the paint is cured (as per specified drying/ curing time), ventilate the tank with warm air, at minimum 23 degrees Celsius for 7 days. Fill the tank 3 times with warm water of minimum 50 degrees Celsius, with each filling remaining in the tank for 24 hours. Finally, either wash the tank with brushes with water of minimum 50 degrees Celsius, or, wash the tank with steam.